

# Superfine Type I

CHEMICAL PARAMETER	SPECIFICATION	
	Type 1	Type 2
Total Zinc (Zn) Content	>98.0 %	>98.0 %
Metallic Zinc (Zn)	>94.0 %	≥94.0 %
Lead (Pb)	<0.15 %	<0.01 %
Cadmium (Cd)	<0.10 %	≤0.01 %
Iron (Fe)	<0.05 %	≤0.02 %
Chloride (Cl)	<0.05 %	≤0.01 %
Physical Parameter	Specification	
	<i>Type 1</i>	<i>Type 2</i>
Particle Size (µm)	2.5 - 4	2.5 - 4
Pack Size	Product packed in 50kg drums or 1000kg bulk bags. Different packing sizes available on request.	

## Application for Superfine Type I & II:

Zinc Dust is most often found in coatings and paints to inhibit corrosion. It is also used by silver and gold mining companies as a precipitant in the recovery process.

The zinc dust is suitable for both organic and inorganic primers. The complete range ensures that the different dry film thickness for a range of zinc primers can be attained.

For more information on this product, contact our sales department on +27 (11) 746 5000.



# ZINCHEM